

Appl. No. 10/083,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

### Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application.

### Listing of the Claims:

1. (Currently Amended) A method for making a modified surface on a polymeric material, the method comprising:
  - ~~- incubating a photo-initiator-coated polymeric material with an aqueous monomer capable of free radical polymerization; and~~
  - ~~— exposing the incubating polymeric material to UV light creating a modified surface on said polymeric material~~
  - incubating a photo-initiator-coated silicone material provided as a device selected from the group consisting of implants, catheters, stents, wound dressings, cardiac valves, tubings, pins and clips with an aqueous monomer solution capable of free radical polymerization and selected from the group consisting of acrylic acid, methacrylic acid, 2-carboxyethyl acrylate, 4-vinylbenzoic acid, itaconic acid, and mixtures thereof, wherein the photo-initiator is selected from the group consisting of p-benzoyl tert-butylperbenzoate, 2,2-dimethoxy-2-phenyl-acetophenone, benzil ketals, benzoin and their derivatives and mixtures thereof;
  - exposing the incubating material to ultraviolet (UV) light creating a modified surface on said material;
  - washing and drying said material with said modified surface.
2. (Cancelled)
3. (Cancelled)

Appl No. 10/083,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

4. (Cancelled)

5. (Cancelled)

6. (Cancelled)

7. (Cancelled)

8. (Cancelled)

9. (Currently Amended) The method of claim 8, wherein said aqueous monomer solution additionally comprises a photo-initiator.

10. (Currently Amended) The method of claim 9, wherein said photo-initiator of said aqueous monomer solution is selected from the group consisting of 2,2-dimethoxy-2-phenyl-acetophenone, p-benzoyl tert-butylperbenzoate and mixtures thereof.

11. (Cancelled) The method of claim 10, further comprising rendering said modified surface lubricious.

12. (Original) The method of claim 11, wherein said modified surface is ionized in an aqueous base to be negatively charged to provide a lubricious surface.

13. (Original) The method of claim 12, wherein said aqueous base is selected from the group consisting of disodium tetraborate, sodium carbonate, ammonium hydroxide, calcium hydroxide, sodium hydroxide and mixtures thereof.

Appl. No. 10/083,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

14. (Original) The method of claim 13, further comprising rendering said lubricious modified surface of said polymeric material antibacterial.

15. (Currently Amended) The method of claim 14, wherein said polymeric material is incubated in an electrolyte solution to saturate the negatively charged surface with cations prior to followed by incubation in a silver salt solution.

16. (Currently Amended) The method of claim 15, wherein said silver salt solution comprises a salt selected from the group consisting of silver lactate, silver phosphate, silver citrate, silver acetate, silver benzoate, silver chloride, silver carbonate, silver iodide, silver iodate, silver nitrate, silver laurate, silver sulfadiazine, silver palmitate, silver benzoate, silver salicylate, silver thiosulfate and mixtures thereof.

17. (Currently Amended) A method for making a modified surface on a polymeric material, the method comprising:

- incubating a photo-initiator-coated polymeric material with an aqueous monomer solution capable of free radical polymerization;
- exposing the incubating polymeric material to ultraviolet (UV) light creating a modified surface on said polymeric material; and
- coating The method of claim 10, wherein said polymeric material with said modified surface is coated with a gelatin polyethylene oxide hydrogel having a silver salt incorporated therein.

18. (Cancelled)

19. (Cancelled)

Appl. No. 10/083,737

Amtd. Dated Jan. 27, 2004

Reply to Office action of Sept. 17, 2003

20. (Cancelled)

21. (Cancelled)

22. (Cancelled)

23. (Currently Amended) A method for making a lubricious anti-microbial modified surface on a polymeric material, the method comprising:

- incubating a photo-initiator-coated polymeric material with an aqueous monomer solution capable of free radical polymerization;
- exposing the incubating polymeric material to ultraviolet (UV) light creating a modified polymeric surface on said polymeric material;
- rendering said modified polymeric surface lubricious; and
- providing a silver agent to said ~~ionized~~ lubricious modified polymeric surface.

24. (Original) The method of claim 23, wherein said polymeric material is selected from the group consisting of polyurethanes, polyamides, polyesters, polyethers, polyorganosiloxanes, polysulfones, polytetrafluoroethylene and polysiloxanes.

25. (Currently Amended) The method of claim ~~24~~23, wherein said polymeric material is silicone.

26. (Original) The method of claim 25, wherein said polymeric material is provided as a device selected from the group consisting of implants, catheters, stents, wound dressings, cardiac valves, tubings, pins and clips.

Appl. No. 10/083,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

27. (Original) The method of claim 26, wherein said monomer is selected from the group consisting of acrylic acid, methacrylic acid, 2-carboxyethyl acrylate, 4-vinylbenzoic acid, itaconic acid, and mixtures thereof.

28. (Currently Amended) The method of claim 27, wherein said photo-initiator is selected from the group consisting of peresters,  $\alpha$ -hydroxyketones, benzil ketals, benzoin and their derivatives and mixtures thereof.

29. (Currently Amended) The method of claim 28, wherein said photo-initiator is selected from the group consisting ~~consisting~~ of 2,2-dimethoxy-2-phenyl-acetophenone, p-benzoyl tert-butylperbenzoate and mixtures thereof.

30. (Currently Amended) The method of claim 23, wherein said aqueous monomer solution additionally comprises a photo-initiator.

31. (Currently Amended) The method of claim 30, wherein said photo-initiator ~~of said aqueous monomer solution~~ is selected from the group consisting of 2,2-dimethoxy-2-phenyl-acetophenone, p-benzoyl tert-butylperbenzoate and mixtures thereof.

32. (Original) The method of claim 31, wherein said silver agent is added by immersing said ionized modified polymeric material in an electrolyte solution having a pH of at least about 8.0 followed by immersion in a silver salt solution.

33. (Original) The method of claim 31, wherein a hydrogel is covalently bound to said modified polymeric surface.

Appl. No. 10/083,737  
 Amdt. Dated Jan. 27, 2004  
 Reply to Office action of Sept. 17, 2003

34. (Original) The method of claim 33, wherein said hydrogel comprises a crosslinked matrix of gelatin and poly (ethylene oxide) sequestering a silver agent.

35. (Original) The method of claim 32, wherein said silver agent comprises a silver salt selected from the group consisting of silver lactate, silver phosphate, silver citrate, silver acetate, silver benzoate, silver chloride, silver carbonate, silver iodide, silver iodate, silver nitrate, silver laurate, silver sulfadiazine, silver palmitate, silver benzoate, silver salicylate, silver thiosulfate and mixtures thereof.

36. (Currently Amended) A method for making a lubricious anti-microbial modified surface on a polymeric material, the method comprising:

- precoating a polymeric material with a photo-initiator;
- immersing the precoated polymeric material in an aqueous solution of vinyl carboxylic acid monomer and exposing the incubating polymeric material to ultraviolet (UV) light to create a modified non-lubricious polyacrylate surface on said polymeric material;
- ionizing said polyacrylate surface of said polymeric material by immersion in an aqueous base to render said surface lubricious;
- saturating the polyacrylate surface with cations by immersion in an electrolyte solution;
- providing silver to said cation-saturated polyacrylate surface.

37. (Original) The method of claim 36, wherein said precoated polymeric material is further washed and dried prior to immersion in monomer.

Appl. No. 10/063,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

38. (Original) The method of claim 36, wherein said polymeric material is selected from the group consisting of polyurethanes, polyamides, polyesters, polyethers, polyorganosiloxanes, polysulfones, polytetrafluoroethylene and polysiloxanes.

39. (Currently Amended) The method of claim 3836, wherein said polymeric material is silicone.

40. (Original) The method of claim 39, wherein said polymeric material is provided as a device selected from the group consisting of implants, catheters, stents, wound dressings, cardiac valves, tubings, pins and clips.

41. (Original) The method of claim 40, wherein said monomer is selected from the group consisting of acrylic acid, methacrylic acid, 2-carboxyethyl acrylate, 4-vinylbenzoic acid, itaconic acid, and mixtures thereof.

42. (Currently Amended) The method of claim 41, wherein said photo-initiator is selected from the group consisting of peresters,  $\alpha$ -hydroxyketones, benzil ketals, benzoin and their derivatives and mixtures thereof.

43. (Currently Amended) The method of claim 42, wherein said photo-initiator is selected from the group consisting consisting of 2,2-dimethoxy-2-phenyl-acetophenone, p-benzoyl tert-butylperbenzoate and mixtures thereof.

44. (Original) The method of claim 43, wherein said aqueous monomer solution additionally comprises a photo-initiator.

Appl. No. 10/083,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

45. (Currently Amended) The method of claim 44, wherein said photo-initiator of said aqueous monomer solution is selected from the group consisting of 2,2-dimethoxy-2-phenyl-acetophenone, p-benzoyl tert-butylperbenzoate and mixtures thereof.

46. (Original) The method of claim 45, wherein silver is provided by immersing said ionized polymeric material in a silver salt solution.

47. (Original) The method of claim 45, wherein silver is provided by covalently binding a hydrogel to said ionized polyacrylate surface, said hydrogel sequestering a silver salt.

48. (Original) The method of claim 46, wherein said silver salt is selected from the group consisting of silver lactate, silver phosphate, silver citrate, silver acetate, silver benzoate, silver chloride, silver carbonate, silver iodide, silver iodate, silver nitrate, silver laurate, silver sulfadiazine, silver palmitate and mixtures thereof.

49. (Original) The method of claim 36, wherein said electrolyte solution has a pH of at least about 8.0.

50. (Original) The method of claim 49, wherein said electrolyte solution is selected from the group consisting of sodium lactate, sodium acetate, sodium citrate, disodium phosphate, potassium acetate, potassium citrate, dipotassium phosphate and mixtures thereof.

51. (Original) The method of claim 50, wherein said electrolyte solution is sodium lactate.



Appl. No. 10/083,737  
Amdt. Dated Jan. 27, 2004  
Reply to Office action of Sept. 17, 2003

52. (New) A method for making a modified surface on a polymeric material, the method comprising:

- incubating a photo-initiator-coated polymeric material with an aqueous monomer solution capable of free radical polymerization;
- exposing the incubating polymeric material to ultraviolet (UV) light creating a modified surface on said polymeric material; and
- rendering said modified surface lubricious.

53. (New) The method of claim 52, wherein said method further comprises providing a silver agent to said lubricious modified surface.